



Formosa Plastics®

Technical Data Sheet

Formolene® HDPE

Formolene E924

Melt Index – 0.04

Density – 0.949

High Molecular Weight High Density Polyethylene (HMW-HDPE) for Film Extrusion

Formolene E924 is a bi-modal HMW-HDPE resin designed for high dart impact strength and good processing characteristics. The resin is well balanced in overall physical properties and provides good stiffness for thin gauge film applications.

Formolene E924 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications

T-Shirt Bags

Trash Can Liners

Industrial liners

Heavy Duty Bags

Nominal Physical Properties

PROPERTY**	TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.949
Melt Index, Condition E,			
Condition E, 190°C/2.16 kg (MI)	D1238	g/10 min.	0.04
Condition F, 190°C/21.6 kg (HLMI)	D1238	g/10 min.	8.50
Melting Point	DSC	°C	131.0
<u>Typical Film Properties</u>			
Dart Impact	D1709	g/mil.	210
Elmendorf Tear Strength	D1922	g/mil.	14/25*
Tensile Strength at Break	D882	psi.	9,000/4,100*
Elongation	D882	%	300/410*

* MD / TD

Note: Film Properties based on 0.50 mil film produced in laboratory conditions at a Blow Up Ratio of 4.0 and a stalk height of 5X the die diameter. Actual film properties may vary depending on operating conditions and additive packages. Film properties are not intended to be used as specifications.

Published 08/04 Rev. 3/09

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

©Formosa Plastics Corporation, U.S.A.

Formolene® is a registered trademark of FPC USA



ISO 9001:2000
FS 70459
FM 31429



ISO 14001:2004
EMS 35710

